



**PROHESIVE**<sup>TM</sup>

**PROSET SUPER**



PROHESIVE<sup>TM</sup> PROSET SUPER is a rigid set, high strength, cement based adhesive used for bonding most types of tiles over masonry substrates. It can be used for both internal and external situations for floor and wall tiling. It is also suitable for continuous immersion applications. PROHESIVE<sup>TM</sup> PROSET SUPER can be mixed with PROHESIVE<sup>TM</sup> PROLASTIC to improve adhesion and increase flexibility.

## PRODUCT FEATURES

- C2 – High bond strength
- T – Non slip / slump
- E – Extended open time
- Self priming
- White
- Easy to use
- Water washable
- Thick and thin bed applications
- Low VOC

## SUITABLE TILE TYPES

- Terracotta
- Slate
- Quarry
- Bicottura
- Monocottura
- Porcelain
- Natural Stone: including marble, granite, limestone and travertine
- Glass mosaics

## AREAS OF USE

- Interior & exterior applications
- Walls & floors
- Concrete
- Sand / cement screeds
- Cement render
- Tiling over waterproofing membranes that have been certified by CTA<sup>TM</sup>\*
- Continuous immersion applications

## SURFACE PREPARATION

### General

Ensure that the surface is dry and clean. Remove any loose material and all contaminants such as grease, oil and dust prior to applying. Make certain that there are no undulations in the surface that may require PROHESIVE<sup>TM</sup> PROSET SUPER to be applied at a thickness in excess of 12mm. If necessary, level floors using ECO SYSTEMS<sup>TM</sup> ECO LEVEL FS.

## PERFORM THE SUBSTRATE TEST

No water absorbed	Mechanically prepare the surface / Use Eco Prep n Prime
Moderate water absorbed	Clean with a damp sponge and fresh water
All water absorbed	Broom on liberal amounts of water

This simple indicative test is performed after vacuuming or sweeping a number of test areas and applying a single drop of fresh drinking water from the end of your finger. This should be approximately 10 to 20mm wide when it first hits the floor – if it beads and remains whole then “No water is absorbed”. If it loses all gloss within 20 to 60 seconds then “Moderate water is absorbed”. If the gloss disappears instantly or within 20 seconds then the substrate has “All water absorbed”. Look for different surface appearances in your floor and test each to ensure your test is representative of the whole area. Perform test in both a cool shaded area and an exposed sunny area if tiling externally.

*\*PROHESIVE<sup>TM</sup> PROSET SUPER must be mixed with undiluted PROHESIVE<sup>TM</sup> PROLASTIC.*

## SUBSTRATES / BACKGROUNDS

### Concrete Floors

Allow at least 28 days for the concrete to cure. Concrete should be left with an open surface – standard helicopter finishes are generally acceptable if they display the “Moderate water absorption” in the substrate test. Wood float or broom finish is preferred where possible. All traces of curing compounds (or sealers) should be removed prior to tiling as these can act as release agents. The surface should be flat and even unless falls are incorporated where required.

### Sand / Cement Screeds and Renders

The screeds and / or renders must conform with the appropriate standard and should be left with a wood float finish and left to cure for at least 7 days per 25mm thickness.

### CTA™ Certified Waterproofing Membranes

Waterproofing membranes must be allowed to cure as per the product's specification.

## MIXING

Pour room temperature, potable water into a clean mixing container before slowly adding the adhesive powder. A 20kg bag of PROHESIVE™ PROSET SUPER will require approximately 4.5 litres of water. Always add powder to the water and mix until a smooth toothpaste consistency is achieved. Allow mixture to stand for 5 minutes to allow the chemicals to slake – then restir and the product is ready for immediate use. **DO NOT ADD MORE WATER.** Restirring may be necessary from time to time within this period.

## APPLYING

- Tiles should be fixed in accordance with Australian Standard AS3958.1 – 2007.
- Ensure the back of each tile is clean and free from dust or other contaminants.
- The adhesive should be applied in areas not exceeding one square metre at a time to ensure the adhesive does not skin prior to fixing. Notch on the adhesive with the correct sized trowel in a straight line avoiding swirls.

- While pressing the tiles into the adhesive, slide them at 90 degrees to the direction of the notches for about the distance of the notch; i.e. 10mm for the 10mm notched trowel. This ensures that the whole back of the tile is in contact with the adhesive.
- It is advisable to remove tiles regularly to check that the whole of the back of the tile has maximum coverage as per the Standard. Contact CTA™ if you are unsure of the requirements. Large tiles may require “back-buttering” to ensure full adhesive contact with the back of the tile.
- All adhesive residue must be removed from the face of tiles, joints and fittings before the adhesive sets.

## OPEN TIME

30 minutes at 23°C and 60% relative humidity.

## POT LIFE

2.5 hours at 23°C and 60% relative humidity.

## CURING

Tiles can accept foot traffic and can be grouted after 24 hours. This is dependent on the density of the background and tiles and the ambient temperature and humidity.

## GROUTING

Tiles should be grouted using the appropriate POLYBLEND™ premium grout. Select colour and range to suit joint width and preferred finish.

## CLEANING

Tools and equipment can be washed using clean water before the adhesive has set.

## INCORPORATING MOVEMENT JOINTS

Movement Joints must be installed according to Australian Standard AS3958.1 - 2007.

## COVERAGE

Notched Trowel Size	Coverage Per 20kg bag
6mm	6.6m <sup>2</sup>
12mm	3.3m <sup>2</sup>

## STORING

When PROHESIVE™ PROSET SUPER is stored in its original unopened package in a dry area at a temperature of 23°C and a relative humidity of 60%, it should be usable for approximately 12 months.

## HANDLING

CTA™ supports best practice in material handling: Gloves, mask and protective clothing should be worn. If the product comes into contact with the skin, wash off with warm soapy water. Avoid inhaling the dust by wearing a dust mask and provide adequate ventilation.

If swallowed drink plenty of water and seek medical advice. In case of contact with the eyes, rinse with an eye wash or wash away with plenty of clean water. For further information refer to product MATERIAL SAFETY DATA SHEET.

## PACK SIZE

Available in 20kg paper bags.

## LIMITATIONS

- PROHESIVE™ PROSET SUPER cannot be used directly over flexible substrates including fibrous cement sheeting, plasterboard, tongue and grooved timber flooring, particleboard, medium density fibreboard or masonite.
- PROHESIVE™ PROSET SUPER is not suitable for use with moisture sensitive tiles or stone.
- PROHESIVE™ PROSET SUPER must not be used directly over solvent based polyurethane waterproofing membranes.
- PROHESIVE™ PROSET SUPER can only be used over high quality water based waterproofing membranes that have been certified by CTA™ when mixed with undiluted PROHESIVE™ PROLASTIC.
- Special fixing techniques are required when tiling externally at heights that exceed 2.7 metres.
- The performance of PROHESIVE™ PROSET SUPER will be compromised when tiling in temperatures below 5°C and above 35°C.
- Suspended concrete slabs intended for tiling must comply with the relevant standard. The use of a flexible adhesive is recommended for applications over post tensioned concrete slabs.
- Contact CTA™ for advice if further information is required.

## WARRANTY

Construction Technologies Australia warrants its products for a period of twelve (12) years from the date of sale. Visit [www.ctaust.com.au](http://www.ctaust.com.au) to view the full terms and conditions of this warranty.

Manufactured by:



**NEW SOUTH WALES**  
2 Prime Drive ( Corner Powers Road)  
Seven Hills NSW 2147  
T 02 9674 1004 F 02 9674 2002

**QUEENSLAND**  
70 Platinum Street  
Crestmead QLD 4132  
T 07 3489 3000 F 07 3489 3099

**WESTERN AUSTRALIA**  
Unit 2 / 51 Wittenberg Drive  
Canning Vale WA 6155  
T 08 9256 1074 F 08 9256 1076

**SOUTH AUSTRALIA**  
PO Box 872  
Brighton SA 5048  
T 08 8387 2356 F 08 8387 9268

**VICTORIA**  
Unit 28/283 Rex Road  
Campbellfield VIC 3061  
T 1300 656 202 F 1300 964 202

**NEW ZEALAND**  
Unit D, 150 Harris Road  
East Tamaki, Auckland  
T +64 9 274 9112 F +64 9 274 6661