


## SikaSwell® S-2

One part polyurethane, extrudable swelling waterstop  
(bentonite-free)

**Description** SikaSwell S-2 is a specially formulated, high-performance, swellable, one-component, polyurethane-based waterstop for use in all kinds of construction joints. Swelling rubber creates a compression seal within joint, blocking the passage of water.

**Where to Use**

- Designed for construction joints in new watertight concrete structures.
- Excellent for sealing pipe penetrations through walls and floor slabs.
- Excellent for sealing joints between precast elements.
- May be applied to horizontal, vertical and overhead surfaces.
- Ideal for watertight construction joints between new and existing concrete.



**Advantages**

- Swells up to 100% in potable water, slightly less in salt water and wastewater.
- Permanently water resistant, with no leaching and does not dissolve in water.
- Capable of sealing construction joints with head pressures of up to 50 psi (115 ft. head).
- Elastic-withstands wet/dry cycling.
- Easy, simple application.
- Adaptable in the field to suit job requirements.
- No nails, glue, or hooks required.
- Controlled expansion eliminates cracking in fresh concrete.
- Offers resistance to various chemicals.
- Thixotropic properties allow SikaSwell S-2 to seal irregular joint surfaces.
- Very economical.
- Saves labor by eliminating inverted keyways, split forming, heat splicing, special fittings and tying to rebar associated with conventional PVC waterstops.
- No mixing required.
- Allows more thorough vibration of concrete at joint, resulting in better concrete consolidation which aids in achieving a watertight joint.

### Typical Data (Material and curing conditions 73°F (23°C) and 50% R.H.)

RESULTS MAY DIFFER BASED UPON STATISTICAL VARIATIONS DEPENDING UPON MIXING METHODS AND EQUIPMENT, TEMPERATURE, APPLICATION METHODS, TEST METHODS, ACTUAL SITE CONDITIONS AND CURING CONDITIONS.

<b>Shelf life</b>	9 months	
<b>Storage Conditions</b>	For best results, store dry at 70°F (20°C) before using.	
<b>Color</b>	Red	
<b>Temperature of Product for Best Application</b>	50° to 90°F	
<b>Tack Free Time</b>	2-3 hours	
<b>Shore A Hardness</b>	Swollen (7 days in tap water)	>10
	Non Swollen (7 days)	40-60
<b>Swelling Capacity</b>	1 day	<20%
	7 days	>100%


Reduced and delayed swelling properties in salty water.

### Suggested Cross Section of Extruded Bead

Concrete Thickness	Number of Beads (in.)	Side length of triangular bead (in.)
8-12	1	5/8
12-20	1	3/4
> 20	2	3/4

**Note:** If the maximum size aggregate in the concrete is greater than 1 inch, use 3/4 inch triangular section(s).

<b>Coverage</b>	20 fl.oz. uni-pac sausage seals: Triangular Yield 5/8 x 5/8 x 5/8 in. 18 lineal ft. 3/4 x 3/4 x 3/4 in. 12 lineal ft. Note: Yield may vary based on substrate irregularities.
<b>Packaging</b>	Disposable 20 fl. oz., moisture-proof uni-pac sausages, 20/carton.
<b>How to Use</b>	
<b>Surface Preparation</b>	Clean all surfaces. Substrate must be clean, sound, free of loose particles, dust, laitance, oils, and other contaminants. Surface may be dry or damp, with no presence of standing water. Do not leave the product in contact with wet concrete, or on a surface with a very high moisture content, for a long period of time, before casting new concrete. These conditions will decrease the adhesion between the SikaSwell S-2 bead and the surface of the joint.
<b>Application</b>	Recommended application temperatures: 50°-90°F. Extrude material using Sika MK-5 bulk caulking gun or other approved bulk gun. Cut the nozzle to obtain a triangular extrusion section with a size fulfilling effective needs (or use nozzle included in carton of SikaSwell S-2). Apply a uniform, continuous bead to the hardened concrete. Wait for approximately 2 hours after placement of the SikaSwell S-2 before placing concrete. The minimum thickness of concrete around the SikaSwell S-2 should be 4 inches on each side (reinforced concrete) or 6 in. on each side (non-reinforced concrete) and 4 inches on top. For optimum application, store at 70°F for a minimum of 8 hours prior to use; if the material appears stiff, knead the sausage for a short time before placing in bulk gun.
<b>Limitations</b>	<ul style="list-style-type: none"> <li>■ Not suitable for expansion joints.</li> <li>■ Protect from rain to avoid expansion before placing new concrete and to assure 100% swelling capacity.</li> <li>■ Avoid placement of the concrete from a height greater than 20 inches. If this is not possible, allow SikaSwell S-2 to cure for 2 days before placing concrete.</li> </ul>
<b>Caution</b>	Avoid skin and eye contact. Use of NIOSH approved organic vapor respirator, safety goggles, and chemical resistant gloves recommended. Remove contaminated clothing and shoes.
<b>First Aid</b>	In case of skin contact, wash thoroughly with soap and water. For eye contact, flush immediately with plenty of water for at least 15 minutes; contact a physician. Wash clothing before re-use. Discard contaminated shoes.
<b>Clean Up</b>	Uncured material can be removed with approved solvent. Cured material can only be removed mechanically. For spillage, collect and dispose of in accordance with current, applicable local, state, and federal regulations.



### SikaSwell S-2 Installation

1. Clean surface of concrete.
2. Cut nozzle to obtain triangular extrusion section (or use nozzle included in carton of SikaSwell S-2).
3. Apply a uniform, continuous bead to hardened concrete. Wait 2 hours before placing new concrete.

**KEEP CONTAINER TIGHTLY CLOSED • KEEP OUT OF REACH OF CHILDREN • NOT FOR INTERNAL CONSUMPTION • FOR INDUSTRIAL USE ONLY**  
All information provided by Sika Corporation ("Sika") concerning Sika products, including but not limited to, any recommendations and advice relating to the application and use of Sika products, is given in good faith based on Sika's current experience and knowledge of its products when properly stored, handled and applied under normal conditions in accordance with Sika's instructions. In practice, the differences in materials, substrates, storage and handling conditions, actual site conditions and other factors outside of Sika's control are such that Sika assumes no liability for the provision of such information, advice, recommendations or instructions related to its products, nor shall any legal relationship be created by or arise from the provision of such information, advice, recommendations or instructions related to its products. The user of the Sika product(s) must test the product(s) for suitability for the intended application and purpose before proceeding with the full application of the product(s). Sika reserves the right to change the properties of its products without notice. All sales of Sika product(s) are subject to its current terms and conditions of sale which are available at [www.sikausa.com](http://www.sikausa.com) or by calling 800-933-7452.

Prior to each use of any Sika product, the user must always read and follow the warnings and instructions on the product's most current Technical Data Sheet, product label and Material Safety Data Sheet which are available online at [www.sikausa.com](http://www.sikausa.com) or by calling Sika's Technical Service Department at 800-933-7452. Nothing contained in any Sika materials relieves the user of the obligation to read and follow the warnings and instruction for each Sika product as set forth in the current Technical Data Sheet, product label and Material Safety Data Sheet prior to product use.

**LIMITED WARRANTY:** Sika warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current Technical Data Sheet if used as directed within shelf life. User determines suitability of product for intended use and assumes all risks. Buyer's sole remedy shall be limited to the purchase price or replacement of product exclusive of labor or cost of labor. **NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. SIKASHALL NOT BELIEVE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. SIKASHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS.**

Visit our website at [www.sikausa.com](http://www.sikausa.com)

1-800-933-SIKA NATIONWIDE

**Regional Information and Sales Centers.** For the location of your nearest Sika sales office, contact your regional center.

**Sika Corporation**  
201 Polito Avenue  
Lyndhurst, NJ 07071  
Phone: 800-933-7452  
Fax: 201-933-6225

**Sika Canada Inc.**  
601 Delmar Avenue  
Pointe Claire  
Quebec H9R 4A9  
Phone: 514-697-2610  
Fax: 514-694-2792

**Sika Mexicana S.A. de C.V.**  
Carretera Libre Celaya Km. 8.5  
Fracc. Industrial Balvanera  
Corregidora, Queretaro  
C.P. 76920  
Phone: 52 442 2385800  
Fax: 52 442 2250537



Sika and SikaSwell are registered trademarks. Printed in Canada.