

BUILDING TRUST

PRODUCT DATA SHEET Sika AnchorFix[®]-1

Fast curing styrene free chemical anchoring adhesive

DESCRIPTION

Solvent and styrene free based, two-component polyester anchoring adhesive.

USES

As a fast curing anchoring adhesive for all grades of: • Rebars / reinforcing steel

- Threaded rods
- Bolts and special fastening systems
- Concrete
- Hollow and solid masonry
- Hard natural stone*
- Solid rock*

* These substrates may vary greatly, in particular with regard to strength, composition and porosity. Therefore, for each application the suitability of Sika AnchorFix®-1 Adhesive must be tested by first applying Sika AnchorFix®-1 Adhesive only to a sample area. Check in particular bond strength, surface staining and discolouration.

CHARACTERISTICS / ADVANTAGES

- Fast curing
- Standard guns can be used
- Can be used at low temperatures
- High load capacity
- ETA Approval available
- Non-sag, even overhead
- Styrene-free
- Low odour
- Low wastage

APPROVALS / CERTIFICATES

- Complies to NCC 2019 reference to AS 5216:2018 -Design of post-installed and cast-in fastenings in concrete
- Injection system for use in masonry according to ETAG 029, ETA-12/0227, Declaration of Performance 020403010010000001 5034408, certified by notified product certification body 0679, certificate of constancy of performance 0679-DPD-0777, and provided with the CE marking
- Bonded injection type anchor for non cracked concrete according to ETAG 001 annex 1 and 5, ETA-13/0720, Declaration of Performance
 020403010010000001 5034408, certified by notified product certification body 1020, certificate of constancy of performance 1020-CPD-090-029816, and provided with the CE marking.

PRODUCT INFORMATION

Packaging	300 ml standard cartridge	12 cartridges per box pallet: 75 boxes	
	550 ml standard cartridge	Project quantities availble on re- quest. Lead times apply.	
Shelf life	12 months from date of production All Sika AnchorFix®-1 cartridges have the expiry date printed on the label.		
Storage conditions	Stored properly in original, unopened, sealed and undamaged packaging ir dry conditions at temperatures between +5 °C and +25 °C. Protect from direct sunlight.		
Colour	Component A:	white	
	Component B:	black	
	Component A+B mixed:	light grey	
Density	~1.63 kg/l (component A+B mixed)		

TECHNICAL INFORMATION

~60 N/mm² (7 days, +20 °C)		(ASTM D 695)
~3 500 N/mm² (7 days, +20 °C)		(ASTM D 695
~28 N/mm² (7 days, +20 °C)		(ASTM D 790)
~12 N/mm² (7 days, +20 °C)		(ASTM D 638)
~4 500 N/mm² (7 days, +20 °C)		(ASTM D 638)
Long term Short term (1–2 hours)	+50 °C +80 °C	
+60 °C		(DIN EN ISO 6721-1)
For details about adhesive anchoring design refer to the separate docu- mentation provided: "Technical Documentation Sika AnchorFix®-1" Ref: 870 43 01		
	 ~3 500 N/mm² (7 days, +20 °C) ~28 N/mm² (7 days, +20 °C) ~12 N/mm² (7 days, +20 °C) ~4 500 N/mm² (7 days, +20 °C) Long term Short term (1–2 hours) +60 °C For details about adhesive and mentation provided: "Technical structure of the structu	\sim 3 500 N/mm² (7 days, +20 °C) \sim 28 N/mm² (7 days, +20 °C) \sim 12 N/mm² (7 days, +20 °C) \sim 4 500 N/mm² (7 days, +20 °C)Long term Short term (1–2 hours) $+$ 50 °C +80 °C+60 °CFor details about adhesive anchoring design refer to mentation provided: "Technical Documentation Sika"

APPLICATION INFORMATION

Mixing ratio	Component A : component B = 10 : 1 by volume 3 mm max.	
Layer thickness		
Sag flow	Non-sag, even overhead	
Material temperature	Sika AnchorFix [®] -1 must be at a temperature of between +5 °C and +40 °C for application.	
Ambient air temperature	-10 °C min. / +40 °C max.	
Dew point	Beware of condensation. Substrate temperature during application must be at least 3 °C above dew point.	
Substrate temperature	-10 °C min. / +40 °C max.	



Temperature	Open time - T _{gel}	Curing time - T _{cur}	
+30 °C	4 minutes	35 minutes	
+25 °C – +30 °C	4 minutes	40 minutes	
+20 °C – +25 °C	5 minutes	50 minutes	
+10 °C – +20 °C	6 minutes	85 minutes	
+5 °C – +10 °C	10 minutes	145 minutes	
+5 °C	18 minutes	145 minutes	
–10 °C 1 2	30 minutes	24 hours	

1 Minimum cartridge temperature: +5 °C

2 This application is not covered by the scope of the product ETA or any other approval.

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

FURTHER INFORMATION

For design details, please refer to the separate documentation provided:

Technical Documentation Sika AnchorFix[®]-1 Ref: 870 43 01

ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

APPLICATION INSTRUCTIONS


SUBSTRATE QUALITY

- Mortar and concrete must be at the required strength. No need to be 28 days old.
- Substrate strength (concrete, masonry, natural stone) must be verified.
- Pull-out tests must be carried out if the substrate strength is unknown.
- The anchor hole must always be clean, dry, free from oil and grease etc.
- Loose particles must be removed from the holes.
- Threaded rods and rebars have to be cleaned thoroughly from any oil, grease or any other substances and particles such as dirt etc.




MIXING

Getting the cartridge ready: 300 ml / 550 ml








2. Cut the film



APPLICATION METHOD / TOOLS

Anchors in solid masonry / concrete







Drilling of hole with an electric drill to the diameter and depth required. Drill hole diameter must be in accordance with anchor size.

The drill hole must be cleaned with a blow pump or by compressed air, starting from the bottom of the hole. (at least 2x)

Important: use oil-free compressors.

The drill hole must be





thoroughly cleaned with the special steel brush (brush at least 2x). The diameter of the brush must be larger than the diameter of the drill hole.


The drill hole must be cleaned with a blow pump or by compressed air, starting from the bottom of the hole. (at least 2x)

Important: use oil-free compressors.

The drill hole must be thoroughly cleaned with the special steel brush (brush at least 2x). The diameter of the brush must be larger than the diameter of the drill hole.



3. Screw on the static mixer




4. Place the cartridge into the gun and start application




When the work is interrupted the static mixer can remain on the cartridge after the gun pressure has been relieved. If the resin has hardened in the nozzle when work is resumed, a new nozzle must be attached.






The drill hole must be cleaned with a blow pump or by compressed air, starting from the bottom of the hole. (at least 2x)


Important: use oil-free compressors.




Pump approx. twice until both parts come out uniformly. Do not use this material. Release the gun pressure and clean the cartridge opening with a cloth.



Inject the adhesive into the hole, starting from the bottom, while slowly drawing back the static mixer.In any case avoid entrapping air. For deep holes extension tubing can be used.





Insert the anchor with a rotary motion into the filled drill hole. Some adhesive must come out of the hole. Important: the anchor must be placed within the open time.




During the resin hardening time the anchor must not be moved or loaded. Wash tools immediately with Sika® Colma Cleaner. Wash hands and skin thoroughly with warm soap water.

Anchors in hollow blocks







drill hole. The drill hole must be cleaned after each cleaning step with a blow pump or by compressed air, starting from the bottom of the hole (pump at least 1x).

Drilling of hole with an

electric drill to the dia-

quired. Drill hole diameter must be in accordance

with anchor-and perforated sleeve size.

Note: with hollow material do not use rotary ham-

The drill hole must be

thoroughly cleaned with a round brush (brush at


least 1x). The diameter of

the brush must be larger than the diameter of the


meter and depth re-

mer drills.

Important: use oil-free compressors.




Insert perforated sleeve completely into the drill hole.




Pump approx. twice until both parts come out uniformly. Do not use this material. Release the gun pressure and clean the cartridge opening with a cloth.







Inject the adhesive into the perforated sleeve, starting from the bottom, while slowly drawing back the static mixer. In any case avoid entrapping air.



Close the cap from the perforated sleeve to avoid some escape of the resin during entering the steel rod.



Insert the anchor with a rotary motion into the filled perforated sleeve. Use the adequate steel rod size. Important: the anchor must be placed within the open time.



During the resin hardening time the anchor must not be moved or loaded. Wash tools immediately with Sika[®] Colma Cleaner. Wash hands and skin thoroughly with warm soap water.

CLEANING OF EQUIPMENT

Clean tools and application equipment with Sika[®] Colma Cleaner immediately after use. Hardened / cured material can only be mechanically removed.

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the declared data for this product may vary from country to country. Please consult the local Product Data Sheet for the exact product data.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Sika Australia Pty Limited ABN 12 001 342 329 aus.sika.com Tel: 1300 22 33 48

Product Data Sheet Sika AnchorFix®-1 April 2023, Version 02.03 020205010010000001 SikaAnchorFix-1-en-AU-(04-2023)-2-3.pdf

BUILDING TRUST

